



SOFT Backer Rod

Patented, round, flexible polyolefin foam rod made of a non-absorbing outer skin and resilient interior network of both open and closed cells that does not out-gas when ruptured.

Features

- Easy to apply
- Non-gassing
- Non-exuding
- Chemically inert
- Virtually dust-free
- Non-absorbing
- Meets all of the requirements of the 1990 Clean Air Act
- Is a "Domestic End Product" as defined in the Buy American Act, Title 41 USC 10

Physical Properties

Property	Value	ASTM Test Methods
Density lb/ft ³ (kg/m ³), avg.	1.8 -2.5 (28-40)	D 1622
Outgassing (No. of Bubbles)	< 1	C 1253
Compression Recovery, %, min	> 95	D 5249
Compression Deflection psi (kPa)	1.2 (8.0)	D 5249
Tensile Strength psi (kPa)	43.4 (299)	D 3575
Water Absorption (g/cc)	< .03	C 1016-Procedure B

Description

Type B- Per ASTM C 1330. Cylindrical, flexible sealant backings composed of bi-cellular material. Also Reference ASTM C 717 for us as gasket or sealing material.
 FORM: Round Foam Rod.
 TEMPERATURE LIMITS: -45 Degree F to +160 Degree F

Benefits

Backer rod limits the depth of the sealant and prevents excessive sealant use. It also helps sealant assume optimum shape factor to prolong sealant service life and acts as a barrier to the flow of sealant through the joint.

Joint Preparation & Installation

Just prior to placing the backer rod, clean all joints per the sealant manufacturer's recommendations. Thoroughly remove any concrete form-release agents, curing compound residue, laitance, or any foreign materials. To ensure a good sealant bond, joints must be clean and dry when the new sealant is installed. Air compressors used for this purpose must be equipped with traps for removal of oil and moisture. Install the backer rod at the depth recommend by the sealant manufacturer with blunt tool.

Size Selection

Proper size selection is important as it controls the depth of the sealant bead. It must be oversized (25%-50%) to fit tightly into the joint and function as a bond breaker to prevent back-side adhesion of the sealant.

Applications

Common applications include, but not limited to, expansion and contraction joints, window glazing, curtain wall construction partitions, parking decks, bridge construction, modular home gasketing, and log home chinking.

Compatibility

Bi-cellular polyolefin foam is basically an inert material; and therefore, it is compatible, both physically and chemically, with virtually all known cold applied sealants, including self-leveling types.

Precautions

Do not puncture, over compress or stretch backer rod during insertion. Do not use with hot applied sealants. Tests for outgassing of cold applied sealants shall be made in accordance with ASTM Test Method C 1253. Sealants compatibility should be confirmed by the sealants in contact with sealant backings can be determined by ASTM Method C 1087.

Although every effort has been made to assure the accuracy of this information and the safety and suitability of its products, BoMetals accepts no responsibility for results obtained by the application of the information or for the safety and suitability of its products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. In view of the various conditions under which this information and our products or products of other manufacturers in combinations with our product may be used, BoMetals sells its products without warranty, and buyers and users assume all responsibility and liability for loss damage from handling and use of these products, whether used alone or in combination with other products.