

PRODUCT DATA SHEET
HydroStrip
HS-201P



Solvent-Free, Hydrophilic, Elastomeric Sealant for Concrete Structures



PHYSICAL PROPERTIES OF HYDROPHILIC ELASTOMERIC SEALANT		
Property	Typical Value	Test Method
Cure System	Hybrid, Moisture Cure	
Cure Rate (77°F at 50% Relative Humidity)	1/8" per 40 hours	
Gun Grade	Zero Slump	ASTM C679
Tensile Strength	159 psi	ASTM D412
Shear Strength	188 psi	ASTM D1002
Elongation	185%	ASTM D412
Adhesion to Primed Concrete (Clean, Dry)	30 pli, cohesive failure	ASTM C794
Shore A, Hardness	35	ASTM D661
UV Stability, Accelerated Weathering	UV-A, No Change (2,000 hours)	QUV Weatherometer
VOC Content	20.6 grams/liter	
Shrinkage	No measureable shrinkage after 14 days	
Service Temperature	-40°F to 220°F (-40°C to 104°C), continuous service	
Application Ambient Temperature	40°F to 130°F (4°C to 55°C)	
Application Surface Temperature	40°F to 130°F (4°C to 55°C)	

Limited Warranty

This information is presented in good faith, but we cannot anticipate all conditions under which this information and our products, or the products of other manufactures in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combinations for their own purposes. It is the users' responsibility to satisfy himself as to the suitability and completeness of such information for this own particular use. We sell this product without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of this product, whether used alone or in combination with other products.

**Where to use HydroStrip
Hydrophilic Elastomeric Sealant**

HS-201P is a waterstop designed for use in cold joints, precast joints, and for use as a bedding adhesive for hydrophilic waterstops – such as HS-1020CR and HS-0725CR. With a hydrostatic pressure resistance of 60 psi, HS-201P can be used in deep construction applications such as: Tunnels, Vent Shafts, and Dams. HS-201P can also be used in more common concrete structures that require a waterstop: Manholes, Box Culverts, Containment Structures, Concrete Slabs or Foundation Joints, Wall or Floor Penetrations, Water & Wastewater Structures, and Many More.

Features

- Finish: Blue, Rubber
- Over 100% hydrophilic expansion in the first 48 hours.
- 250% hydrophilic expansion in 30 days.
- Solvent & Isocyanate Free, 100% solids, will not shrink.
- Tack free skin is formed in 60 minutes (@ 75°F / 23°C)
- Full cure takes place in 24 to 48 hours (service coats < 100 mils).
- Excellent weatherability when exposed to: Ultraviolet Radiation, Rain, Infrared Radiation, & Atmospheric Hydrocarbons. Limited service in alkaline and hydrocarbon solutions. Contact Concrete Sealants, Inc. for additional information.
- Superior adhesion to most construction materials, including: Concrete, Metal, Fiberglass, Many Plastics, PVC, Glass, Aluminum and Wood Contact Concrete Sealants, Inc. for additional application possibilities.

KEEP OUT OF REACH OF CHILDREN

141 Hammond Street
Carrollton, GA 30117

Phone 770-832-2000 • 800-862-4835 • FAX 770-832-2095
Visit our website @ www.bometals.com
Address email to info@bometals.com

Founded in 1989, BoMetals has become an industry leader in the design and manufacture of concrete and masonry accessories.